



# ENVIRONMENTAL CATEGORIES



# ENVIRONMENTAL CATEGORIES AND PRODUCT RECOMMENDATIONS

## INTRODUCTION

New Zealand has a wide range of environmental conditions, from the harsh West Coast beaches, to the relative shelter of the Waikato farming region. Therefore, New Zealand Steel Limited offers a range of steel products which are suitable for most locations.

### VERY SEVERE – ISO CATEGORY 5

50m from high water on East Coast, 100m from high water on West Coast.

Characterised by:

- Heavy salt deposits.
- The almost constant smell of salt spray in the air.
- Close to breaking surf (typically 50-100 metres) such as is found on exposed coasts.

This environment may be extended inland by prevailing winds and local conditions.

Roofing.....

Wall Cladding.....

Gutters/downpipes.....

Fascia.....

### SEVERE – ISO CATEGORY 4

Characterised by:

- Light salt deposits.
- A frequent smell of salt in the air.
- Typically starts 100-500 metres from breaking surf such as is found on exposed coasts.
- In the immediate vicinity of large expanses of calm salt water such as harbour foreshores.

This environment may be extended inland by prevailing winds and local conditions.

Roofing.....

Wall Cladding.....

Gutters/downpipes.....

Fascia.....

### MODERATE COASTAL – ISO CATEGORY 3

Characterised by:

- Little or no salt deposits.
- The occasional smell of salt in the air.
- Typically starts 500-1000 metres from breaking surf such as is found on exposed coasts, OR in the immediate vicinity of calm salt water such as estuaries.

### MODERATE INLAND – ISO CATEGORY 2

Characterised by:

- No obvious marine or industrial influences.
- Typically more than 1000 metres from the exposed coasts or more than 500 metres from industrial emissions.

Roofing.....

Wall Cladding.....

Gutters/downpipes.....

Fascia.....

## COMMERCIAL WARRANTY

Such as schools, warehouses and buildings, refer to New Zealand Steel Limited for details of commercial warranties. Maximum warranty offered on commercial buildings is 15 years.

## IMPORTANT

- As product use is dictated by local conditions, seek advice from your roofing supplier or fixer for the best New Zealand Steel Limited product to suit your specific environment.
- Gutters should be installed according to manufacturer's instructions.
- Unwashed and high risk areas – manual washing every 3 months.

0 metres

50 metres

Greater than 50m from breaking surf on the East Coast.  
Greater than 100m from breaking surf on the West Coast.

## WARRANTIES

**15 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

**15 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

**10 years:** covering the paint surface against flaking, peeling and excessive fade. **10 years:** against perforation as a result of corrosion.

**10 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

## MAINTENANCE

- Rain washing
- Rain washing plus manual washing every 3 months.
- Manual washing every month.
- Manual washing every month.

**15 years:** covering the paint surface against flaking, peeling and excessive fade. **20 years:** against perforation as a result of corrosion.

**15 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

**10 years:** covering the paint surface against flaking, peeling and excessive fade. **10 years:** against perforation as a result of corrosion.

**10 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

- Rain washing
- Rain washing plus manual washing every 6 months.
- Manual washing every 3 months.
- Manual washing every 3 months.

**15 years:** covering the paint surface against flaking, peeling and excessive fade. **30 years:** against perforation as a result of corrosion.

**15 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

**10 years:** covering the paint surface against flaking, peeling and excessive fade. **10 years:** against perforation as a result of corrosion.

**10 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

- Rain washing
- Rain washing plus manual washing every year.
- Manual washing every 6 months.
- Manual washing every 6 months.

## WARRANTIES

Not recommended

## MAINTENANCE

Not recommended

**15 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

Not recommended

**5 years:** covering the paint surface against flaking, peeling and excessive fade. **10 years:** against perforation as a result of corrosion.

**5 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

- Rain washing
- Rain washing plus manual washing every 6 months.
- Manual washing every 3 months.
- Manual washing every 3 months.

**18 years:** covering the paint surface against flaking, peeling and excessive fade. **30 years:** against perforation as a result of corrosion.

**15 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

**10 years:** covering the paint surface against flaking, peeling and excessive fade. **10 years:** against perforation as a result of corrosion.

**10 years:** covering the paint surface against flaking, peeling and excessive fade. **15 years:** against perforation as a result of corrosion.

- Rain washing
- Rain washing plus manual washing every year.
- Manual washing every 6 months.
- Manual washing every 6 months.

VERY SEVERE COASTAL

100 metres

SEVERE COASTAL

500

WARRANTIES

Not recommended

MAINTENANCE

Not recommended

WARRANTIES

No warranty

MAINTENANCE

Not recommended

Not recommended

Not recommended

No warranty

Not recommended

**15 years:** against perforation as a result of corrosion.

- Rain washing

No warranty

- Rain washing

**15 years:** against perforation as a result of corrosion.

- Rain washing plus manual washing every 6 months.

**10 years:** against perforation as a result of corrosion.

- Manual washing every 3 months.

**10 years:** against perforation as a result of corrosion.

- Manual washing every 3 months.

- Rain washing plus manual washing every 6 months. Painting may be advisable depending on the specific location.
- Manual washing every 3 months. Painting may be advisable depending on the specific location.
- Manual washing every 3 months. Painting may be advisable depending on the specific location.

MODERATE COASTAL

MODERATE INLAND

metres

1000 metres



In New Zealand there are areas where local conditions create an increased likelihood of corrosion. Special consideration should be given to material selection in these areas. They include:

**1. Geothermal Areas**

Hydrogen sulphide associated with geothermal activity creates a corrosive environment. Variations in natural activity or draw-off from steam bores plus the effects of weather conditions make the high risk areas hard to define.

**2. West Coast, South Island**

In this area, smoke from the coal burning fires may cause high concentrations of sulphur dioxide in the air. The combination of this and the high rainfall for the region creates an aggressive situation which must be considered when choosing the appropriate COLORSTEEL® prepainted steel coating. The effects of a severe coastal environment aggravate the situation.

This area combines the most severe features of both industrial and coastal environments. Please contact your local supplier for the best COLORSTEEL® prepainted steel product to use.

**3. Internal Environments**

Some commercial or agricultural applications may create internal environments in which the build-up of pollutants or fumes is a potential source of corrosion. Similarly a corrosive environment can develop within sheds used for intensive animal farming. Please consult New Zealand Steel Limited for further details.

**4. Industrial Environments**

Close to corrosive industrial emissions and subject to heavy fallout from them. Please consult New Zealand Steel Limited for further details.

**Further Assistance**

Further advice on the selection of the appropriate product to suit your particular location can be obtained from New Zealand Steel Limited or your local COLORSTEEL® prepainted steel supplier.



**VERY SEVERE SPECIAL ENVIRONMENTS**



## FURTHER INFORMATION

For additional information, literature or technical assistance, please contact:

COLORSTEEL® and ZINCALUME® Marketing  
New Zealand Steel Limited  
Private Bag 92 121, Auckland 1142  
Telephone: 0-9-375 8999  
Facsimile: 0-9-375 8213  
Free Phone: 0800 100 523  
Email Address: [info@colorsteel.co.nz](mailto:info@colorsteel.co.nz)  
<http://www.colorsteel.co.nz>

## Zincalume®

ZINCALUME® is a registered trademark.

## GALVSTEEL™

GALVSTEEL™ is a trademark of  
New Zealand Steel Limited.

## COLORSTEEL® Maxx™

COLOUR FOR THE EXTREME

MAXX™ is a trademark of New Zealand Steel Limited.

## COLORSTEEL® Endura™

COLOUR FOR THE FUTURE

ENDURA™ is a trademark of New Zealand Steel Limited.

## COLORSTEEL®

COLORSTEEL® is a registered trademark  
of New Zealand Steel Limited.

## COLORSTEEL®

## THE ROOF OF NEW ZEALAND®

is a registered trademark of New Zealand Steel Limited.

**NOTE:** With New Zealand Steel Limited's commitment to continuous improvement, information provided in this publication may be subject to modification. At the time of publication we believe the information contained in this document is the best available. Nonetheless, we reserve the right to modify any product, technique, equipment or statement to reflect improvements in the manufacture and application of coil coated products. The information is supplied without prejudice to New Zealand Steel Limited's standard terms and conditions of sale. In the event of any conflict between this information and the standard terms and conditions, the standard terms and conditions shall prevail.

This edition of the New Zealand Steel Environmental Categories Guide supersedes all previous editions.

Copyright© 2010 New Zealand Steel Limited.

NEW ZEALAND STEEL  
100% RECYCLABLE



Kiwi to the core

## COLORSTEEL®

## THE ROOF OF NEW ZEALAND®



New Zealand Steel Limited, Private Bag 92 121, Auckland 1142, New Zealand. Ph 0-9-375 8999 Fax 0-9-375 8213